

MEĎ

EN		STN/ČSN		DIN		ASTM
CW004A	Cu-ETP	423001	Cu99,9E	2.0060	E-Cu57/E-Cu58	C11000
CW006A	Cu-FRTP	423003	Cu99,85	2.0090	SF-Cu	C12500
CW008A	Cu-OF	423000	Cu99,95	2.0040	OF-Cu	C10200
CW021A	Cu-HCP	~	~	2.0070	SE-Cu	C10300
CW024A	Cu-DHP	423003	Cu99,85	2.0090	SF-Cu	C12500
CW101C	CuBe2	~	~	2.1247	CuBe2	C17200
CW103C	CuCo1NiBe	~	~	2.1285	CuCoNiBe	C17500
CW104C	CuCo2Be	~	~	2.1285	CuCo2Be	C17500
CW106C	CuCr1Zr	423039	~	2.1293	CuCrZr	C18150
CW111C	CuNi2SiCr	423054	~	2.0855	CuNi2SiCr	C64700
CW022A	Cu-PHC	~	~	2.0070	SE-Cu 58	C10300
CW009A	Cu-OFE	~	~	2.0040	Cu-OFE	C10100
CW023A	Cu-DLP	~	~	2.0076	SW-Cu	C12000