

MOSADZ

EN		STN/ČSN	DIN		ASTM
CW600N	CuZn36Pb1,5	423214	2.0331	Ms 63 Pb	C35300
CW505L	CuZn5	423200	2.0220	Ms 95	C21000
CW501L	CuZn10	423201	2.0230	Ms 90	C22000
CW502L	CuZn15	423202	2.0240	Ms 58	C23000
CW503L	CuZn20	423203	2.250	Ms 58	C24000
CW508L	CuZn37	423213	2.0321	Ms 63	C27200
CW505L	CuZn30	423210	2.0265	Ms 70	C26000
CW509L	CuZn40	423220	2.0360	~	C28000
CW602N	CuZn36Pb2As	~	~	~	C35330
CW606N	CuZn37Pb2	~	~	~	C35300
CW607N	CuZn38Pb1	~	~	~	C35000
CW608N	CuZn38Pb2	423222	2.0371	Ms60 Pb (Cu Zn38 Pb1,5)	C37700
CW610N	CuZn39Pb1	423222	2.0372	CuZn39Pb0,5	C36500
CW612N	CuZn39Pb2	~	2.0380	Ms 58	C37700
CW614N	CuZn39Pb3	423223	2.0401	Ms 58	C38500
CW617N	CuZn40Pb2	423223	2.0402	~	C38010
CW618N	CuZn40Pb2AL	~	2.0550	~	C38000
CW706R	CuZn28Sn1As	423239	2.0470	~	C44300
CW713R	CuZn37Mn3Al2PbSi	~	2.0550	So- Ms58 Al2 (Cu Zn40 Al2)	C67420
CW715R	CuZn38SnAl	~	2.0525	~	C47000
CW717R	CuZn38Sn1	423237	2.0530	~	C46400